



TECHNICAL SHEET ART. BLACKBURN

Description Boot in Eco Leather, black color , warm lining 80% polyester and 20% acrylic , non-metallic insole lining HRP INSOLE, Thermo-Plus Insole with a high thermal isolation, double density polyurethane sole, bending resistant, abrasion resistant, oil resistant, slip resistant, antistatic

Plus Midsole compound particularly studied to get a soft PU density for a higher comfort

Suggested sectors of usage Chemistry/Food , Building/costruction, petrochemical industry, oil & gas industry, naval industry , mineral Industry , cold Enviroment, mineral industry, professional/ craftsman

Care and Maintenance Clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source



Class: S3 CI SRC
 Sizes: 36-48
 Instep: 12
 Weight(±10%): 649 gr. (*)

Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirement
Toe cap: Top Composite toe cap, impact resistant 200 J	5.3.2.3	Impact resistance	mm	15,5	>= 14
	5.3.2.4	Compression resistance	mm	15,0	>= 14
Midsole: non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100	>= 1.100
Antistatic footwear: dissipation capacity of the electrostatic charge	6.2.2.2	Electric resistance			
		- Wet	MOhm	11,3	>= 0,1
		- Dry	MOhm	43	<= 1000
Capacity of energy absorption in the heel area	6.2.4	Energy absorption in the heel area	J	32,0	>= 20
Upper: Eco Leather water-repellent, black color, thickness 2,0 mm	5.4.6	Water vapour permeability	mg/cmq h	1,8	>= 0,8
		Coefficient of permeability	mg/cmq	17,2	>= 15
	5.4.3	Tearing Strength	N	90	>= 60
Vamp lining and quarter lining: warm lining 80% polyester and 20% acrylic	5.5.3	Water vapour permeability	mg/cmq h	5,6	>= 2
		Coefficient of permeability	mg/cmq	46,4	>= 20
	5.5.1	Tearing Strength	N	23	>= 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
Insole lining: textile anti perforation midsole HRP Insole	5.7.3	Water Absorption	Mg/cm ²	78	>= 70
		Ability to release water		99%	>= 80%
Sole: Double density polyurethane, bending resistant, abrasion resistant, oil resistant, slip resistant, antistatic	5.8.2	Tearing Strength	kN/m	11,5	>= 8
	5.8.3	Abrasion resistance	mm ³	50	<= 150
	5.8.4	Bending resistance	mm	1,5	<= 4
	5.8.5	Hydrolysis	mm	2,5	<= 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	-0,6%	<= 12%
	5.11	Slip resistance on ceramic floor with water and detergent	flat	0,43	>= 0,32
			inclined	0,40	>= 0,28
		Slip resistance on steel floor with glycerine	flat	0,21	>= 0,18
			inclined	0,15	>= 0,13

Blackburn style and its components: no presence of dangerous substances by Annex VII to regulation no. 1907/2006/CE and subsequent amendments and additions

(*) = Indicative weight that refers to ½ pair in size 42